




R11

FABCON 2FC/6 TR14 00/00 FA

KC2TR1401

TECHNICAL INFORMATION

	IMPERIAL	METRIC
Max Production Width	118.11in	3000mm
Total Thickness	0.06in	1.4mm
Mass	0.29lb/ft ²	1.4kg/m ²
Tensile force at 1% elongation (static)	34lb/in Internal Method - ref. ISO 21181	6N/mm
Working Temp.	+14/+158F ^o	-10/+70C ^o
Flexion (A)	0.59in 15mm	
Counter Flexion (B)	0.59in 15mm	

COEFFICIENT OF FRICTION (bottom side) - **Steel** 0.24

BEST USED FOR

GENERAL CHARACTERISTICS

2 ply bare by bare PVC. Food approved. Cotton-polyester mix fabrics.

RECOMMENDED USES

Slider Bed | Flat Rollers | Slider Beds on Both Sides | Channel Trough | Conveyor with Accumulation | Slide Bed with Pressure | Bend Conveyor

SPECIAL CHARACTERISTICS

- ✓ **Food Approved, FDA compliance**
acc.to 21 CFR parts 170-19
- ✓ **Food Approved, EU compliance**
(EC) No. 1935/2004 & (EU) No. 10/2011

BELT CONSTRUCTION INFORMATION



TOP SIDE (Carrying)		TENSION MEMBER	BOTTOM SIDE (Pulley)		
Material	Polyester-Cotton	Interply	PVC	Material	Polyester-Cotton
Color	Fabric (FA)	Weft	Flexible (F)	Color	Fabric (FA)
Thickness	0in 0mm	Plies	2	Thickness	0in 0mm
Hardness ISO 868	-	Fabric	Flexible Cotton (FC)	Hardness ISO 868	-
Surface	Bare (00)			Surface	Bare (00)

*Because of continuous development above data is subjected to change without prior notice by Sampla. This data replaces that included in previous publications. Sampla excludes any liability for the incorrect use of the above stated information.

RELEASED 01/01/2019